



BIRLA WHITE TILELYNK

Finish mast.
Pakad Zabardast.



TILELYNK - TILE GROUT

Birla White TileLynk is a high quality, advanced polymer -modified, high performance grout with excellent water repellent and efflorescence resistance properties. Birla White TileLynk has higher strength and more water and stain resistance compared to normal cement grout.



DURABLE AND FLEXIBLE



FOR TILE JOINTS 1-6 MM GAP



HIGHEST WATER RESISTANCE



Features and Advantages:

- Ready to use; and only onsite mixing with water is required.
- Can be used for both interior and external applications.
- Can be used for filling up to 6 mm grout width.
- Gives non shrink, water and UV resistant grouting results.

Suitable for:

Grouting glazed tiles, mosaic, vitrified and fully vitrified tiles, ceramic tiles, industrial tiles, granites, marbles and other natural stones etc.

Packaging: 1 kg bag

Technical Specifications:

Pot Life	EN 13888-1-2022	*Shelf life	Colour
1hrs.	CG-2WA	12 months	White

PROPERTIES AS PER EN 13888 -1 - 2022 (CG-2WA)	Test Method	Requirement	Test Results
1. Compressive Strength – Dry, N/mm ²	EN 13888	≥ 15	> 22
2. Compressive Strength – Freeze Thaw Cycle, N/mm ²	EN 13888	≥ 15	> 18
3. Flexural Strength – Dry, N/mm ²	EN 13888	≥ 2.5	> 6
4. Flexural Strength – Freeze Thaw Cycle, N/mm ²	EN 13888	≥ 2.5	> 5
5. Water Absorption after 30 minutes, gms	EN 13888	< 2	< 1.6
6. Water Absorption after 240 minutes, gms	EN 13888	< 5	< 3.7
7. Shrinkage, mm/m	EN 13888	< 3	< 0.2
8. Abrasion Resistance, mm ³	EN 12808	≤ 1000	< 800

*For sealed pack when stored under cover, out of direct sunlight, damp-proof condition and protect from extremes of temperature.

Physical Properties @ 25°C

Variant	TileLynk
Mixing Ratio by weight	0.34 - 0.36
Mixed Density, kg/liter	1.65 - 1.85
Pot Life, hours	1
Sag Resistance	Non-Sag
Setting Time, hours	24
Time to Foot Traffic, hours	24
Time to Heavy Traffic, hours	7 days
Width Thickness, mm	Up to 6 mm
Application Temperature (Substrate and Materials), °C	5 - 35





Scan to
Know More

Birla White - A Unit of UltraTech Cement Limited,

9th Floor, Birla Centurion, Pandurang Budhkar Marg,
Worli, Mumbai - 400030

🌐 Website: www.birlawhite.com | 📞 Toll Free No.: 1800 11 1717

📘 www.facebook.com/BirlaWhiteCement | 🐦 twitter.com/BirlaWhite

✉ bw-consumercare@adityabirla.com