

TILESTIX INTERO GRIP+

It is a polymer modified, White Cement-based thin-set tile adhesive for fixing ceramic, semi-vitreous tiles and small to medium format natural stones.



DURABLE



**HIGHER
ADHESION**



EASE OF USE



TILE ON TILE



Features and Advantages:

- Can be used in internal areas, for floor as well as wall applications.
- Water resistant - suitable for wet areas.
- Sag resistant formula provides hassle-free application on vertical walls.
- Low VOC for healthy living.

Suitable for:

Horizontal surfaces and vertical surfaces up to a height of 3 meters, over the cementitious substrate for indoor application in dry as well as wet areas. It is also recommended for tile-on-tile application.

Packaging: 20 kg bag

Technical Specifications:

Pot Life	Tensile Adhesion	Shear Adhesion	**Coverage	IS 15477: 2019	EN 12004: 2017	*Shelf life
2hrs.	> 0.8 N/mm ²	> 1.10 N/mm ²	Approx. 55-60 ft ²	Type 1'T'	Type C1T	12 months

*For sealed pack when stored under cover, out of direct sunlight, damp-proof condition and protect from extremes of temperature.

**Coverage will vary depending on trowel notch size, type and size of tile and substrate smoothness and evenness. For 20 kg bag at 3 mm thickness using 6 mm x 6 mm square notched trowel.

Application Areas:

Interior Floors	
Ceramic Tiles	✓
Semi Vitreous	✓
Tile On Tile	✓
Vitrified Tiles	
Porcelain Tiles	
Glass Mosaics	
Natural Stones - Granite/Marble	
Small Format Tiles	✓
Medium Format Tiles	
Large Format Tiles	
Interior Wall	
Up to 9ft	✓

Physical Properties @ 25°C

Variant	Intero Grip+
Mixing Ratio by weight	0.24 - 0.26
Mixed Density, kg/liter	1.60 - 1.80
Open Time, minutes (IS 15477: 2019)	Approx. 20
Adjustability, minutes (IS 15477: 2019)	Approx. 20
Pot Life, hours	2
Setting Time, hours	24
Time to Heavy Traffic, hours	24
Adhesive Thickness, mm	3 - 12
Application Temperature (Substrate and Materials), °C	5 - 35



Properties As Per IS 15477: 2019

Variant	Intero Grip+	
Conforms to:	1T	
Testing Properties	Requirement	Test Results
1. Tensile Adhesion Strength		
a) Dry Condition, N/mm ²	Minimum 0.5	>0.8
b) Wet Condition, N/mm ²		
2. Shear Adhesion Strength		
a) Dry Condition, N/mm ²	Minimum 1.0	>1.10
b) Wet Condition, N/mm ²		
3. Slip Resistance, mm	≤ 0.5	<0.3

Properties As Per EN 12004: 2017

Variant	Intero Grip+	
Conforms to:	C1T	
Testing Properties	Requirement	Test Results
1. Open Time	≥ 0.5	>0.6
@ 20 minutes, N/mm ²		
2. Slip Resistance, mm	≤ 0.5	<0.3
3. Tensile Adhesion Strength		
a) Initial, N/mm ²	≥ 0.5	>0.8
b) After Water Immersion, N/mm ²	≥ 0.5	>0.7
c) After Heat Aging, N/mm ²	≥ 0.5	>0.8
d) After Freeze-Thaw Cycles, N/mm ²	≥ 0.5	>0.7



BIRLA WHITE TILESTIX RANGE



Use Birla White Tilelynk for excellent results.



Scan to
Know More

Birla White - A Unit of UltraTech Cement Limited,

9th Floor, Birla Centurion, Pandurang Budhkar Marg,
Worli, Mumbai - 400030

🌐 Website: www.birlawhite.com | 📞 Toll Free No.: 1800 11 1717

📘 www.facebook.com/BirlaWhiteCement | 🐦 twitter.com/BirlaWhite

✉ bw-consumercare@adityabirla.com